

Crystal chemistry of the crandallite, beudantite and alunite groups: a review and evaluation of the suitability as storage materials for toxic metals

Uwe KOLITSCH* and Allan PRING**

**Institut für Mineralogie und Kristallographie, Geozentrum
Universität Wien, Althanstr. 14 A-1090 Wien, Austria*

***Department of Mineralogy, South Australian Museum, North
Terrace Adelaide, South Australia 5000, Australia*

The crandallite, beudantite and alunite (jarosite) mineral groups are reviewed, with an emphasis on the evaluation of their suitability as storage materials for toxic metals. New data on the highly flexible crystal chemistry, crystallography and thermodynamic stability fields of both natural and synthetic members are summarised and critically discussed. These compounds can safely incorporate a large number of toxic and radioactive metals. Extensive solid solubilities have been observed. The majority of the members are characterised by very low solubilities over a wide range of pH and Eh conditions, and by high temperature stabilities (up to 400–500°C). It is suggested, also by comparison with other mineral waste hosts (apatites, pyrochlores), that these materials can be favourably used for the long-term fixation and immobilisation of toxic ions of elements such as As, Pb, Bi, Hg, Tl, Sb, Cr, Se, and of radioactive isotopes of K, Sr, Th, U and REE.

Introduction

The crandallite $[\text{CaAl}_3(\text{PO}_4)_2(\text{OH},\text{H}_2\text{O})_6]$, beudantite $[\text{PbFe}_3(\text{AsO}_4)(\text{SO}_4)(\text{OH},\text{H}_2\text{O})_6]$ and alunite (jarosite) $[\text{KAl}_3(\text{SO}_4)_2(\text{OH})_6 (\text{KFe}_3(\text{SO}_4)_2(\text{OH})_6)]$ groups belong to the alunite supergroup, a large family of minerals and synthetic analogues, all of which share the basic, rhombohedral structure type of alunite, $\text{KAl}_3(\text{SO}_4)_2(\text{OH})_6$ (Wang et al., 1965; Menchetti and Sabelli, 1976). The pronounced crystal-chemical versatility of this supergroup is expressed by the general formula $AB_3(XO_4)_2(\text{OH},\text{H}_2\text{O})_6$, where A =mono-, di-, tri- or tetravalent cation, B =trivalent cation, and minor amounts of certain di- and pentavalent cations, and X =penta-, hexavalent cations and minor Si^{4+} .

In view of recent data on alunite-type compounds, their use as storage materials (minerals) for toxic and

radioactive metals is suggested and their suitability as stable host structures for these metals will be discussed in the present review. The underlying concept of this “synthetic mineral immobilisation technology” (SMITE) is very old (Hatch, 1953) and currently a variety of mineral structure types are employed or have been proposed for the incorporation of various waste materials (the following list is not intended to be exhaustive):

For the immobilisation of high level nuclear wastes, the well-known Synroc ceramic matrix, consisting of the titanates zirconolite, $\text{CaZrTi}_2\text{O}_7$, hollandite, $\text{Ba}(\text{Al},\text{Ti})_2\text{Ti}_6\text{O}_{16}$, and perovskite, CaTiO_3 , has been proposed and successfully tested (e.g., Ringwood et al., 1979; Jostons and Kesson, 1994). It is able to safely incorporate radioactive elements from the lanthanide and actinide series, as well as Cs, K, Sr and others, but is yet to be adopted by the nuclear industry for the permanent disposal of waste. Apatite-type compounds are used to remove heavy metal contaminants from wastewater, aquatic solutions and soils, to stabilise toxic metals in

waste dumps and to immobilise radioactive waste (e.g., Suzuki et al., 1985; Gauglitz et al., 1992; Ma et al., 1993; Xu and Schwartz, 1994; Carpena and Lacout, 1997; Traina and Laperche, 1999). A synthetic ceramic matrix designated Xtaltite has been devised to deal with Pb-, As- and Sb-rich ore smelter wastes in Australia; in a hydrometallurgical treatment Ca is added to the primary waste materials and a calcining process produces a ceramic composed of apatite-type $(\text{Pb,Ca})_5(\text{AsO}_4)_3(\text{OH,Cl})$ (corresponding to calcian hydroxyl-mimetite) and pyrochlore-type $\text{Ca}_2\text{Sb}_2\text{O}_7$ (corresponding to romeite) (e.g., White and Kyle, 1995; White et al., 1995). Selected zeolites are employed to decontaminate water and wastewater by incorporating toxic (radioactive) metal cations and radionuclides such as ^{137}Cs and ^{90}Sr (e.g., Mumpton, 1999; Ghobarkar et al., 1999). Hydrated oxysalts with layered structures can be used for the immobilisation of toxic components migrating in urban and other waste dumps, such as Cr ions or halogens (Pöllmann, 1994a, b).

Still, each year huge amounts of waste containing toxic metal compounds (especially of As, Bi, Hg, Pb, Sb, Se, Tl, and radioactive elements) are produced in the form of smelter furnace wastes, galvanic sludges, incinerator ashes, red muds, flue-gas desulphurisation products, rests/byproducts of paint and pesticide production, et cetera. These wastes are difficult or impossible to economically recycle and to store safely.

Our condensed, up-to-date review will first briefly discuss the crystal chemistry of the crandallite, beudantite and alunite mineral groups, including new results from analyses of natural and synthetic members. This is followed by a summary of the widely varying types of natural occurrences, which will illustrate how the compounds act as natural reservoirs of toxic metals and barriers of their further spreading into the environment. Recent data on thermodynamic stability fields and the crystallography will also be addressed. Finally, current and possible uses are reported and the suitability for a long-term fixation of toxic metals is discussed by comparison with other, well-characterised storage minerals.

Crystal chemistry

Members of the crandallite, beudantite and alunite (jarosite) groups form part of the large supergroup of natural and synthetic compounds with the alunite-type structure. Their general formula is $AB_3(\text{XO}_4)_2(\text{OH,H}_2\text{O})_6$, where A =monovalent (H_3O , Na, K, Rb, Ag, Tl, ...), divalent (Ca, Sr, Ba, Pb, Hg, ...), trivalent (Bi, rare earth element=REE) or

tetravalent cation (Th, Zr), B =trivalent cation (Al, Fe, Cr, ...) and minor Cu^{2+} , Zn^{2+} , Sb^{5+} , Nb^{5+} , Ta^{5+} , and $X=\text{P}^{5+}$, As^{5+} , S^{6+} , Se^{6+} , Cr^{6+} and minor Si^{4+} (Hintze, 1933; Palache et al., 1951; Dutrizac et al., 1981; Jambor and Dutrizac, 1985; Lottermoser, 1990; Schwab et al., 1990; Lengauer et al., 1994; Mandarino, 1999; Kolitsch et al., 1999a). The hydroxyl group in the formula can be replaced by minor amounts of Cl^- and F^- . Typical examples are alunite, $\text{KAl}_3(\text{SO}_4)_2(\text{OH})_6$, jarosite, $\text{KFe}_3(\text{SO}_4)_2(\text{OH})_6$, beudantite, $\text{PbFe}_3(\text{AsO}_4)_2(\text{OH,H}_2\text{O})_6$, dussertite, $\text{BaFe}_3(\text{AsO}_4)_2(\text{OH,H}_2\text{O})_6$, crandallite, $\text{CaAl}_3(\text{PO}_4)_2(\text{OH,H}_2\text{O})_6$, plumbogummite, $\text{PbAl}_3(\text{PO}_4)_2(\text{OH,H}_2\text{O})_6$, synthetic $\text{Hg}_{0.5}\text{Fe}_3(\text{SO}_4)_2(\text{OH})_6$, synthetic, $\text{NaAl}_3(\text{CrO}_4)_2(\text{OH})_6$ and synthetic, $\text{KCr}_3(\text{SO}_4)_2(\text{OH})_6$. Pronounced solid solubility phenomena are widespread in natural samples (e.g., Wise, 1975; Scott, 1987; Rattray et al., 1996; Birch and van der Heyden, 1997; Hochleitner and Fehr, 1996; Jambor, 2000; Scott, 2000). Different and contradictory nomenclatory schemes for the naturally occurring compounds have been developed (Scott, 1987; Novák et al., 1994) and an improvement of the current, insufficient nomenclature has recently been proposed by Jambor (1999). The suggested improvement was the subject of further discussion (Jambor, 2000; Scott, 2000).

Unusual elements in alunite-type compounds

New chemical-analytical data on natural and synthetic members demonstrate that several elements can be incorporated into the alunite-type structure which were previously unknown to show such behaviour. The elements currently known to occur in non-negligible amounts in alunite-type compounds are listed in Table 1.

The work of Kolitsch et al. (1999a) on an Sb-rich variety of dussertite, the Ba-Fe-arsenate member of the crandallite group, suggests that, contrary to previous ideas, the structure type may accommodate significant amounts of Sb^{5+} , which is substituting for cations on the B site, but not for As^{5+} on the X site. Small, but distinct contents of Sb have also been found in the Pb-members beudantite and segnitite (Kolitsch, 1999). An Sb-bearing Pb-Fe-arsenate member additionally contained very small amounts of W^{6+} (Kolitsch, unpublished semiquantitative EDS analyses), which is assumed to replace the Fe^{3+} on the B site, as was shown for other ferric iron minerals (Kolitsch, 1998).

Considerable amounts of chromium (6.3 wt.% CrO_3) have been found in the natural Pb-member philipsbornite by Walenta et al. (1982), who assumed

Table 1. Cations occurring in natural and synthetic alunite-type compounds (arranged in order of increasing cation valency; cations most dominant in minerals are underlined)

<i>A</i>	<i>B</i>	<i>X</i>
H ₃ O ⁺	Cu ²⁺ (minor)	Si ⁴⁺ (minor)
NH ₄ ⁺	Zn ²⁺ (minor)	C ⁴⁺ ¹²⁾
<u>Na</u> ⁺	Co ²⁺³⁾	
<u>K</u> ⁺	Ni ²⁺³⁾	<u>As</u> ⁵⁺
Rb ⁺	Mg ²⁺³⁾	<u>P</u> ⁵⁺
Tl ⁺	Mn ²⁺³⁾	
Ag ⁺		<u>S</u> ⁶⁺
	<u>Al</u> ³⁺	Se ⁶⁺¹³⁾
<u>Ca</u> ²⁺	<u>Fe</u> ³⁺	Cr ⁶⁺¹⁴⁾
<u>Sr</u> ²⁺	Cr ³⁺⁴⁾	
<u>Ba</u> ²⁺	Ga ³⁺⁵⁾	
<u>Pb</u> ²⁺	In ³⁺⁶⁾	
Hg ²⁺	V ³⁺⁷⁾	
Bi ³⁺	Ge ⁴⁺⁸⁾	
<u>LREE</u> ³⁺¹⁾		
	Sb ⁵⁺⁹⁾ (minor)	
Th ⁴⁺ , U ⁴⁺ , Zr ⁴⁺²⁾ (minor)	Nb ⁵⁺ , Ta ⁵⁺¹⁰⁾ (minor)	
	W ⁶⁺¹¹⁾ (minor)	

Note: References for most of the individual compounds are given in Lengauer et al. (1994) and in the text of the present work. Specific references are: ¹⁾ LREE = light rare earth elements; the presence of some Sm²⁺ on the *A* site has been proposed by Mordberg et al. (2000); ²⁾ Landa et al. (1995); ³⁾ Typical jarosite wastes from zinc hydrometallurgical processes also contain minor Mg and Mn, and traces of Cd according to Simoncini et al. (1997), but confirmation is required; concerning Cd behaviour see also text. Very minor Co, Ni and Mn can be incorporated in synthetic plumbojarosite (Dutrizac and Dinardo, 1983); ⁴⁾ Lengauer et al. (1994); Johan et al. (1995); Bottrill (pers. comm., 1998) (see text); ⁵⁾ Tananaev et al. (1967a, b), Dutrizac (1984), Bernstein (1986), Kamoun et al. (1989), Jambor et al. (1996), Dutrizac and Chen (2000); ⁶⁾ Dutrizac (1984), Dutrizac and Dou Mingmin (1993); ⁷⁾ Kolitsch et al. (1999c) and references therein; ⁸⁾ Jambor et al. (1996) (see text for discussion); ⁹⁾ Kolitsch (1999); Kolitsch et al. (1999a); ¹⁰⁾ Lottermoser (1990); ¹¹⁾ Kolitsch (unpublished semiquantitative EDS analyses; see text); ¹²⁾ questionable according to Jambor (1999); ¹³⁾ Leclerc (1980), Dutrizac et al. (1981), Dutrizac (1984), Breitingner et al. (1997); ¹⁴⁾ Cudennec and Bonnin (1977), Dutrizac (1984).

that the Cr substitutes for As and S and suggested that the *X* site in the *XO*₄ group is occupied by (As_{1.57}Cr_{0.40}S_{0.10})_{Σ2.07}. However, according to recent analyses of other philipsbornite samples containing considerable Cr, there is strong evidence that Cr is present as Cr³⁺ and substitutes Al by up to 50 at.% (Bottrill, pers. comm.). Up to 18% Cr³⁺ on the *B* site

have been reported in natural gorceixite (Johan et al., 1995). Trace amounts of Cr have also been detected in a natural plumbojarosite (Pring et al., 2000). Although no alunite-type chromate end members are known in natural environments, synthetic chromate members have been reported (see Lengauer et al., 1994).

Other rare and unusual elements have also been reported recently in alunite-type minerals. A Se-rich, beudantite-related Pb-Fe-arsenate-sulphate member from a Se-rich deposit (Baccu Locci mine, Sardinia; Gramaccioli et al., 1997) has been identified recently (Kolitsch, unpublished semiquantitative EDS analyses and X-ray powder diffraction data). A sample of a natural Pb-member, beudantite, from a Czech locality contained In, substituting for Fe, in the range of 1–3 wt.% (Sejkora, pers. comm.). Synthetic In³⁺-members have also been reported and a complete solid solution between NaIn₃(SO₄)₂(OH)₆ and NaFe₃(SO₄)₂(OH,H₂O)₆ was observed (Dutrizac and Dou Mingmin, 1993). Trivalent gallium ions are dominant on the *B* site in gallobeutantite, PbGa₃(AsO₄,SO₄)(OH,H₂O)₆, and other Ga-dominant members have been identified in the gallobeutantite-bearing assemblage as part of complex chemically zoned crystals (Jambor et al., 1996). Gallium was also found to be concentrated in jarosite and limonite as result of a study on the distribution of Ga and Ge in the oxidation zone of a sulphide deposit (Bernstein, 1986). Synthetic Ga³⁺-sulphate members have been prepared by Tananaev et al. (1967a, b) and Dutrizac (1984), and complete solid solubility between *M*Ga₃(SO₄)₂(OH)₆ and *M*Fe₃(SO₄)₂(OH,H₂O)₆ (where *M* = Na, K or NH₄) was demonstrated (Kamoun et al., 1989; Dutrizac and Chen, 2000). Interestingly, the gallobeutantite mentioned above was also found to be Ge-bearing, and Jambor et al. (1996) suggest the Ge⁴⁺ to substitute for the octahedrally coordinated Ga³⁺. However, as Ge⁴⁺ can occur in both 4- and 6-fold coordination, it could also substitute for the As/S (a similar behaviour is known from Si which is commonly found in very small amounts in phosphate and arsenate members). Small amounts of Nb⁵⁺ and Ta⁵⁺ on the *B* site were detected in crandallite-group minerals from rare-earth ore deposits (Lottermoser, 1990). The first naturally occurring V³⁺-dominant member of the alunite supergroup, springcreekite [Ba(V³⁺,Fe³⁺)₃(PO₄)₂(OH,H₂O)₆], has been described recently (Kolitsch et al., 1999c). In natural gorceixite, BaAl₃(PO₄)₂(OH,H₂O)₆, a considerable substitution of V³⁺ for Al³⁺ has been reported (Johan et al., 1995). No vanadates with the alunite-type structure are known, a fact which may be explained by the too large size of the V⁵⁺ ion for the *X* site.

Recent analyses of natural Pb-members from an unusual assemblage of Cd-bearing secondary minerals from Broken Hill, New South Wales, Australia, demonstrate that these Pb-members do not incorporate the toxic Cd (Kolitsch et al., in prep.). This confirms laboratory studies demonstrating that Cd^{2+} is not selectively adsorbed onto or incorporated in the (pure sulphate) jarosite phase (Dutrizac and Weatherell, 1989; Dutrizac et al., 1996), and that only very small amounts of Cd may be incorporated into hydrometallurgically precipitated jarosites (Simoncini et al., 1997).

In summary, Table I shows that the title compounds can incorporate the following large number of toxic or radioactive metals: Tl, Sr, Pb, Hg, Bi, REE, Th, Cr, Se, Sb, As. They may also be able to fixate U, although this is yet to be established. On the other hand, the alunite-type does not seem to be able to incorporate the toxic Cd or radioactive isotopes of the very large Cs (Dutrizac and Jambor, 1987a). The synthesis of chemically pure Hg jarosite would be very difficult, however, as the compound is stable only in a very narrow pH range; Hg jarosite has also not yet been found in nature (Dutrizac and Chen, 1981).

Occurrences and thermodynamic stabilities

Alunite-type sulphates, phosphates and arsenates are widespread in a very large variety of natural geological environments. As stable weathering products of the rock-forming minerals monazite and apatite, phosphates of the crandallite group are common forms of terrestrial soil and sediment phosphate (Norris, 1968; Nriagu, 1984). In these soils the minerals often contain high amounts of trace elements such as Pb, Cu, Cr, etc. (Norris, 1968). Lead arsenate-sulphates were also noted in arsenic-rich soils (e.g., Presant and Tupper, 1966). Other occurrences were recorded in medium-grade metamorphic rocks, hydrothermal veins, greisens, pegmatites, bauxites and laterites, coals and carbonatites, as well as placer deposits and marine sandstones (e.g., Spötl, 1990; Morteani and Ackermann, 1996; Rasmussen, 1996; Rasmussen et al., 1998; Baldwin et al., 2000). Heavy metal phosphate, arsenate and sulphate members are common as secondary minerals in the oxidised zones and gossans of ore deposits, where they limit the further migration of heavy metal ions (e.g., Scott, 1987; Birch and van der Heyden, 1997; Levy et al., 1997; Kolitsch and Elliott, 1999). Sulphate members commonly occur in acid mine-drainage (e.g., Alpers et al., 1994), and it is known that jarosite compounds quickly crystallise wherever highly acidic, naturally formed or anthropogenic aqueous solutions are present in areas of

active or abandoned mining of Fe-bearing sulphide ores (e.g., Alpers et al., 1989; Lin and Herbert, 1997). Numerous investigations showed that these compounds readily incorporate a large range of different metal impurities. Tl-, Pb-, As-bearing and -fixating jarosite has been observed as a secondary, anthropogenic compound in dumps of roasted pyrite ores (Bambauer et al., 1987). The preferred incorporation of Tl in jarosite (and iron oxide) under processes of extreme oxidation and acid leaching has also been reported from a natural occurrence (Scorgie, 1991).

In mining-related acidic lakes, dense crusts of jarosites can serve as a natural self-seal (Schuiling and Van Gaans, 1997). Jarosite waste was produced in a smelter in Australia since 1973 and shipped to a government chosen ocean disposal site. It did not cause any harmful effects on the environment, as extensive monitoring and investigation for over 20 years, including sediment and fish surveys, have demonstrated (Sanderson and Wilson, 1994). Anthropogenic lead phosphate members are found in the vicinity of roads and highways where they form from leaded petrol consumed by automobiles. In these occurrences the compounds serve as a naturally formed host for toxic Pb, therefore reducing the output and spread of anthropogenic Pb into ecosystems (Nriagu, 1984; Eighmy et al., 1999; Morin et al., 2001).

As shown by the wide variety of geological occurrences, some of the title compounds can form at temperatures as low as $\sim 10^\circ\text{C}$ and some are stable up to about 500°C . Observed and deduced pH values for conditions of formation range between <1 and 10 . The compounds form under strongly oxidising to (rarely) slightly reducing conditions. Laboratory studies have shown that both phosphate and arsenate members of the crandallite group exhibit extremely low solubilities (Norris, 1968; Schwab et al., 1993; Roca et al., 1999), with the arsenates being thermodynamically more stable. Crandallite itself, previously considered to be stable only in the presence of impurities (Schwab et al., 1990), has been shown to be a stable phase in the system $\text{CaO-Al}_2\text{O}_3\text{-P}_2\text{O}_5\text{-H}_2\text{O}$ at 200°C (Yuh and Rockett, 1981). The relative stabilities of various alkali jarosites were investigated by Dutrizac (1983) who demonstrated that jarosite, $\text{KFe}_3(\text{SO}_4)_2(\text{OH})_6$, is the most stable among these. Thermodynamically stable, pure synthetic alkali jarosites can incorporate an only very limited amount of arsenate substituting for sulphate (Dutrizac and Jambor, 1987b).

Thermodynamic data are comparatively scarce, however, and stability fields of only few alunite-type minerals have been evaluated (Brown, 1971; Hladky

and Slansky, 1981; Yuh and Rockett, 1981; Stoffregen and Cygan, 1990, and references cited therein; Baron and Palmer, 1996a, b).

Several theoretical end members (such as, for instance, the Ba-Fe- and Ca-Fe-phosphate representatives) do not seem to be stable, probably caused by unfavourable size relationships between the constituent *A*, *B* and *X* cations. The pure theoretical end member $\text{Pb}_{0.5}\square_{0.5}\text{Al}_3(\text{SO}_4)_2(\text{OH})_6$ is unknown from geologic environments, although synthetic $\text{Pb}_{0.5}\square_{0.5}\text{Al}_3(\text{SO}_4)_2(\text{OH})_6$ has been prepared in an autoclave using a hydrothermal technique (Okada et al., 1987), indicating that this compound may be stable only at elevated pressures. The related alunite-type Pb-sulphate osarizawaite, $\sim \text{Pb}(\text{Al}, \text{Cu})_3(\text{SO}_4)_2(\text{OH})_6$ (with Al:Cu at least $\sim 2:1$, and some Al being replaced by Fe), may be considered a Cu(+Fe?)-stabilised variety of the pure Pb-Al-sulphate end member (see also Dutrizac, 1984; Jambor, 1999). It is predicted that more natural members of the alunite supergroup will be found in nature, particularly in geologically unusual environments.

Crystallography

Almost all of the members of the crandallite, beudantite and alunite groups crystallise in the rhombohedral space group $R\bar{3}m$ first established for alunite (Hendricks, 1937; Wang et al., 1965; Menchetti and Sabelli, 1976). The basic structure of an alunite-type compound $AB_3(XO_4)_2(\text{OH}, \text{H}_2\text{O})_6$ consists of sheets of corner-sharing BO_6 octahedra parallel to the basal pinacoid $\{0001\}$ (Fig. 1). Located in-between the sheets are small to very large, generally 12-coordinated *A* cations (e.g., Na, Ca, Pb, Hg), and the sheets themselves are corner-linked to XO_4 tetrahedra (Fig. 1). Hexagonal unit-cell parameters *a* and *c* lie in the ranges 6.97–7.44 and 16.2–17.8 Å, respectively (see also detailed listing of unit-cell data in Lengauer et al., 1994). Due to partial or complete ordering of divalent *A* cations, the *c* axes in some sulphate members are doubled (e.g., plumbojarosite, $\text{Pb}_{0.5}\square_{0.5}\text{Fe}_3(\text{SO}_4)_2(\text{OH})_6$). There is also a currently unique, unnamed natural phosphate member, $\text{PbFe}_3(\text{PO}_4)_2(\text{OH}, \text{H}_2\text{O})_6$, whose crystal structure exhibits a distortion at the Pb sites, leading to two independent Pb atoms in the structure, and a doubling of the *c* axis (Jambor, 1999, 2000).

Few exceptions are known, in which the symmetry of an alunite-type compound is or is assumed to be slightly lower than rhombohedral. This is most probably caused by a disordered or split arrangement of *A*-cations [disordered Ca in crandallite, Blount, 1974; Ba




Figure 1. The alunite-type structure exemplified by the atomic arrangement of (a) hinsdalite, $\text{PbAl}_3[(\text{PO}_4, \text{SO}_4)]_2(\text{OH}, \text{H}_2\text{O})_6$, in a projection along the *c*-axis (Kolitsch et al., 1999b) (note that the Pb atom is disordered), and (b) alunite $\text{KAl}_3(\text{SO}_4)_2(\text{OH})_6$ (Menchetti and Sabelli, 1976) projected approximately along the a_2 -axis and perpendicular to the *c*-axis; the H-bonding scheme is indicated with dashed lines between H atoms (small spheres) and O atoms (medium-large spheres). ATOMS drawings (Shape Software, 1999).

in monoclinic gorceixite (space group *Cm*), Radoslovich and Slade, 1980; Radoslovich, 1982; Blanchard, 1989; K in monoclinic jarosite (space group $C2/m$), Göttlicher and Gasharova, 1999; disordered Na in natrojarosite, Gasharova et al., 2000; see also Kolitsch et al., 1999a]. Symmetry reduction has also been observed in several Pb-members, in which the reduction is due to the off-centre position of the Pb^{2+} ion caused by its $6s^2$ lone pair of electrons (for details see Kolitsch et al., 1999b, and references cited therein). Recently, Hochleitner and Fehr (1998) and Fehr et al. (2000) investigated the Pb-members plumbojarosite, $\text{Pb}_{0.5}\square_{0.5}\text{Fe}_3(\text{SO}_4)_2(\text{OH})_6$, and beudantite $\text{PbFe}_3[(\text{AsO}_4, \text{SO}_4)]_2(\text{OH}, \text{H}_2\text{O})_6$, by Mössbauer spectroscopy and found indications for the presence of two different Fe^{3+} positions. This observation corresponds with Raman spectroscopical data of Sasaki et al. (1998) who reported the presence of two

different SO_4^{2-} positions in plumbojarosite, one adjacent to Pb^{2+} and the other adjacent to the vacancy.

Other indications for small deviations from perfect rhombohedral symmetry in investigated samples are suggested by a fairly large number of reports on anomalous biaxial optics (e.g., Hintze, 1933; Palache et al., 1951; Walenta, 1966; Szymański, 1985). Some of these inferred very small deviations from rhombohedral (hexagonal) symmetry are obviously not detectable by X-ray methods. Strain due to inhomogeneous chemical compositions (often encountered in alunite-type minerals) probably plays an important role in reducing the symmetry (cf. Foord and Mills, 1978). The anomalies may be caused by very small deviations of metal and oxygen atoms from their ideal positions, or by ordering of hydroxyl ions and water molecules. Precession photographs of a sulphate-rich, optically distinctly biaxial negative benuaite, $\text{SrFe}_3[(\text{PO}_4, \text{SO}_4)]_2(\text{OH}, \text{H}_2\text{O})_6$, gave sharp diffraction patterns with a perfectly hexagonal symmetry, suggesting that the dominant scattering components in the investigated crystal occupy their ideal positions (Kolitsch, in prep.). Strong evidence for monoclinic symmetry of a synthetic jarosite prepared at 200°C has been given by Göttlicher and Gasharova (1999), based on the observation of split reflections in X-ray powder diffraction patterns and a single-crystal structure refinement, which indicated space group $C2/m$.

A disordered distribution of cations is firmly established for the *B* site (disordered Al^{3+} , Fe^{3+} and Cu^{2+} in osarizawaite; Giuseppetti and Tadini, 1980). A recent refinement of the structure of an Sb-rich dussertite, $\text{Ba}(\text{Fe}^{3+}_{0.84}, \text{Sb}^{5+}_{0.16})_3(\text{AsO}_4)_2(\text{OH}, \text{H}_2\text{O})_6$, shows that Fe^{3+} and Sb^{5+} are also completely disordered on their shared site (Kolitsch et al., 1999a). Disorder of V^{3+} and Fe^{3+} on the *B* site has been found in the new crandallite-group member springcreekite, $\text{Ba}(\text{V}^{3+}, \text{Fe}^{3+})_3(\text{PO}_4)_2(\text{OH}, \text{H}_2\text{O})_6$ (Kolitsch et al., 1999c).

Disorder on the *X* site has been observed for various mixed P/As/S-members (e.g., Kato and Miura, 1977; Szymański, 1988; Giuseppetti and Tadini, 1989; Kharisun et al., 1997; Kolitsch et al., 1999b). Reported ordering of P/S in corkite, leading to the non-centrosymmetric space group $R3m$ (Giuseppetti and Tadini, 1987), is considered doubtful (for discussions, see Kharisun et al., 1997, Kolitsch et al., 1999b). Obvious ordering of As/S has been reported for gallobendantite which was also attributed space group $R3m$ (Jambor et al., 1996).

Transmission electron microscope (TEM) studies, involving selected area electron diffraction (SAED), of a hinsdalite (Kolitsch et al., 1999b), an arsenatian corkite,

an arsenatian plumbojarosite and a synthetic thallium jarosite (Kolitsch, unpublished results) showed that all investigated samples give sharp reflection spots. No superstructures or deviations from the reported symmetries were observed within error limits.

No information is available on the exact nature of the disorder on the *B* and *X* sites. However, statistical disorder is highly probable as the *B* and *X* cations are tightly bonded to oxygen atoms. The possibility of dynamical disorder can not be excluded for some of the hydrogen atoms. Neutron diffraction or specialised spectroscopic methods may be useful to shed more light on disorder and possible local, short-range ordering. Although neutron diffraction studies were conducted on jarosite compounds they focused on the magnetic properties at very low temperatures (Inami et al., 1998), or on the localisation of H atoms, the nature of the H bonds and the content of oxonium cations (Schukow et al., 1999; investigation of synthetic alunites).

Various spectroscopic methods used to characterise alunite-type compounds (mostly sulphates) comprise infrared spectroscopy (e.g., Adler and Kerr, 1965; Rossman, 1976; Arkhipenko and Bokii, 1979; Serna et al., 1986; Breitingner et al., 1997, 1999), Raman spectroscopy (Serna et al., 1986; Breitingner et al., 1997; Sasaki et al., 1998; Gasharova et al., 2000), Mössbauer spectroscopy (e.g., Afanasev et al., 1974; Leclerc, 1980; Lakshmi Reddy et al., 1991; Vedanand et al., 1992; Hochleitner and Fehr, 1998, Fehr et al., 2000), magnetic susceptibility studies (e.g., Rossman, 1976; Harrison et al., 1997; Earle et al., 1999), and nuclear magnetic resonance spectroscopy (Bleam et al., 1989) as well as optical absorption and electron paramagnetic resonance spectroscopy (Rossman, 1976; Lakshmi Reddy et al., 1991; Vedanand et al., 1992). The cited authors predominantly investigated the local environment and site symmetry of atoms or polyhedra in their samples.

Current and suggested use of alunite-type compounds

Current use of alunite-type compounds is restricted. After heat treatment, Ca- and Sr-phosphates are used as fertilisers (Gilkes and Palmer, 1983). All natural compounds can be used as indicator minerals in exploration (e.g., Nriagu, 1984). High proton conductivity at ambient temperature has been found in hydrated pressed discs of hydronium alunite, $(\text{H}_3\text{O})\text{Al}_3(\text{SO}_4)_2(\text{OH})_6$ (Wing et al., 1980). In hydrometallurgical processes developed in zinc and nonferrous hydrometallurgical plants of the zinc industry, controlled precipitation of jarosite-type compounds is widely used to remove unwanted iron and heavy metal ions (e.g., Dutrizac and Kaiman, 1976;

Dutrizac, 1984). Detailed laboratory-scale studies of these processes have been conducted (e.g., Dutrizac, 1983; Jambor and Dutrizac 1983; Dutrizac, 1984). It was demonstrated, for example, that thallium preferentially enters the structure of jarosite by comparison to sodium and ammonium (Dutrizac, 1997), in agreement with data from natural environments (see above); therefore, jarosite precipitation provides an effective means of eliminating thallium from zinc (and possibly other) processing circuits. The natural Tl-dominant end member is known from a Tl-As deposit ($\text{Tl}_{0.8}\text{K}_{0.2}\text{Fe}_3(\text{SO}_4)_2(\text{OH})_6$, Balić Žunić et al., 1994). The chromate analogue of jarosite, on account of its high thermodynamic stability, may be used to remove Cr(aq) from chromium-contaminated water resources (Baron and Palmer, 1996b).

A novel technique for treating and recycling hydrometallurgical jarosite wastes has been reported recently by Simoncini et al. (1997). The technique is based on self-propagating reactions within a mixture of the jarosite waste materials and added aluminium and ferric oxide. Industrial jarosite waste arising from the hydrometallurgical processing of zinc-rich ores can also be recycled, resulting in Fe-rich glasses and glass-ceramics (e.g., Karamanov et al. 1999). Further use of these wastes is made by the production of new construction materials (Mymrin and Vazquez Vaamonde, 1999).

Crandallite group minerals were recently shown to be suitable for the safe incorporation of radioactive fission products (Ballhorn et al., 1989). This suitability had previously been suggested (Fron del, 1958), and it is also indicated by the crystal-chemical behaviour and long-term stability of natural REE phosphate members in uranium deposits, where they preferentially incorporated fission products (light REE, Zr) from natural nuclear reactor zones and limited their migration (e.g., Janeczek and Ewing, 1996; Dymkov et al., 1997; Gorshkov and Artyukhina, 1997). Landa et al. (1995) showed that, when jarosite was precipitated in the presence of trace amounts of thorium, a significant amount of thorium ('78%') was incorporated in the precipitate. Crandallite-type compounds are easily synthesised and very efficient in separating cations, especially radioactive ones, from aqueous solutions (patent by Brunner et al., 1987).

Advantages of alunite-type compounds

The outstanding crystal-chemical flexibility of the alunite structure allows a large variety of elements with very different sizes and valencies to be incorporated, as already reported by us earlier (Kolitsch and Pring, 1998).

Furthermore, complete or extensive solid solubility among end members is widespread and pronounced disorder of cations on the *A*, *B* and *X* sites facilitates the combined incorporation of different elements (metals). Accordingly, one could describe the alunite structure type as a "garbage-can" structure type, similar to the apatite structure type. Unlike "established" waste storage materials with the apatite-type structure, alunite-type compounds are able to incorporate Sb. On the other hand, the apatite structure can host about 50 different elements (e.g., Roy et al., 1978).

Relatively high thermodynamic stability up to 400–500°C and good chemical resistance over a large range of pH conditions have been established for the majority of the alunite-type compounds. Pb-members such as plumbogummite are especially stable (Schwab et al., 1993) and phosphate and arsenate members have very low solubilities. By contrast with apatite, the Ca-phosphate member crandallite is insoluble under neutral and alkaline conditions and cation exchange is only possible on surface positions (Fron del, 1958). The preparation of crandallite-type compounds by hydrothermal methods is fairly easy (e.g., Brunner et al., 1987; Ballhorn et al., 1989; Schwab et al., 1990). Numerous publications on natural occurrences of phosphate and arsenate members show that these readily form pseudomorphs after lead members of the apatite group. Therefore, they might be considered as a waste form possibly comparable or superior to apatites.

Interestingly, there exists a close relation between the alunite and the pyrochlore structure types (Goreaud and Raveau, 1980). Some of a large number of compounds with the pyrochlore structure have been used as storage materials for the incorporation of certain heavy metals (see Introduction). It is also worth noting that the alunite structure is strongly related to that of the Ca-Fe-phosphate mitridatite (Moore, 1974; Moore and Araki, 1977).

An obvious disadvantage of (Al- and Fe-dominant) alunite-type compounds are the relatively low waste-loading factors imposed by the stoichiometry. Nonetheless, components which would have to be added to produce a final waste storage material, are cheap (e.g., Fe- and Al-bearing precursor materials or solutions). The thermal stability does not exceed temperatures of approximately 400–500°C and is therefore lower than that of "established" storage materials such as apatites or perovskites. However, temperatures in either over- or underground toxic metal waste-dump sites would be well below 150°C.

Conclusions

Members of the crandallite, beudantite and crandallite groups are suggested to have great potential as stable and reliable hosts for toxic metals, on account of their high crystal-chemical variability, general stability and easiness of formation and preparation. Their potential in safely incorporating toxic metals is considered comparable to that of other well-characterised host structures (apatite, perovskite, pyrochlore).

Acknowledgements

C. Lengauer is thanked for helpful comments on the manuscript. The present work also benefitted from careful reviews by R. Miyawaki and an anonymous referee. Financial support to the first author (U.K.) by a Feodor-Lynen-Fellowship of the Alexander-von-Humboldt-Foundation, Bonn, Germany, is gratefully acknowledged. Part of the funds for this Fellowship were granted by the Australian Research Council.

References

- Adler, H.H. and Kerr, P.F. (1965) Variations in infrared spectra, molecular symmetry and site symmetry of sulfate minerals. *American Mineralogist*, 50, 132-147.
- Afanasev, A.M., Gorobchenko, V.D., Kulgawczuk, D.S. and Lukasevich, I.I. (1974) Nuclear gamma-resonance in iron sulphates of the jarosite group. *Physica Status Solidi A*, 26, 697-701.
- Alpers, C.N., Blowes, D.W., Nordstrom, D.K. and Jambor, J.L. (1994) Secondary minerals and acid mine-water chemistry. In *Environmental geochemistry of sulfide mine-wastes* (Jambor, J.L. and Blowes, D.W. Eds.). Mineral. Association Canada, Short-Course, 22, 247-270.
- Alpers, C.N., Nordstrom, D.K. and Ball, J.W. (1989) Solubility of jarosite solid solutions precipitated from acid mine waters, Iron Mountain, California. *Science Geological Bulletin*, 42, 281-298.
- Arkhipenko, D.H. and Bokii, G.B. (1979) Refinement of the space group of alunite-jarosite by means of vibrational spectroscopy. *Soviet Physics Crystallography*, 24, 54-58. (translated from *Kristallografiya*, 24, 100-106)
- Baldwin, J.R., Hill, P.G., von Knorring, O. and Oliver, G.J.H. (2000) Exotic aluminium phosphates, natromontebrazite, brazilianite, goyazite, gorceixite and crandallite from rare-element pegmatites in Namibia. *Mineralogical Magazine*, 64, 1147-1164.
- Balič Žunič, T., Močlo, Y., Lončar, Ž., Micheelsen, H. (1994) Dorallcharite, $Tl_{0.8}K_{0.2}Fe_3(SO_4)_2(OH)_6$, a new member of the jarosite-alunite family. *European Journal of Mineralogy*, 6, 255-263.
- Ballhorn, R., Brunner, H. and Schwab, R.G. (1989) Artificial compounds of the crandallite type; a new material for separation and immobilization of fission products. *Materials Research Society Symposium Proceedings*, 127 (Scientific Basis of Nuclear Waste Management, 12), 249-252.
- Bambauer, H.-U., Steffes-Tun, W. and Krause, C. (1987) Jarosit als Thallium-Träger in einer Deponie von Schwefelkiesabbränden. *Fortschritte der Mineralogie*, 65, Beiheft No. 1, 10.
- Baron, D. and Palmer, C.D. (1996a) Solubility of jarosite at 4-35°C. *Geochimica et Cosmochimica Acta*, 60, 185-195.
- Baron, D. and Palmer, C.D. (1996b) Solubility of $KFe_3(CrO_4)_2(OH)_6$ at 4 to 35°C. *Geochimica et Cosmochimica Acta*, 60, 3815-3824.
- Bernstein, L.R. (1986) Geology and mineralogy of the Apex germanium-gallium mine, Washington County, Utah. *U. S. Geological Survey Bulletin*, U. S. Geological Survey, Reston, VA, USA, 9 pp.
- Birch, W.D. and van der Heyden, A. (1997) Minerals of the Kintore and Block 14 open cuts at Broken Hill, New South Wales. *Australian Journal of Mineralogy*, 3, 23-71.
- Blanchard, F.N. (1989) New X-ray powder data for gorceixite, $BaAl_3(PO_4)_2(OH)_6 \cdot H_2O$, an evaluation of d-spacings and intensities, pseudosymmetry and its influence on the figure of merit. *Powder Diffraction*, 4, 227-230.
- Bleam, W.F., Pfeffer, P.E. and Frye, J.S. (1989) ^{31}P solid-state nuclear magnetic resonance spectroscopy of aluminium phosphate minerals. *Physics and Chemistry of Minerals*, 16, 455-464.
- Blount, A.M. (1974) The crystal structure of crandallite. *American Mineralogist*, 59, 41-47.
- Breitinger, D.K., Krieglstein, R., Bogner, A., Schwab, R.G., Pimpl, Th.H., Mohr, J. and Schukow, H. (1997) Vibrational spectra of synthetic minerals of the alunite and crandallite type. *Journal of Molecular Structure*, 408-409, 287-290.
- Breitinger, D.K., Schukow, H., Belz, H.-H., Mohr, J. and Schwab, R.G. (1999) Two-phonon excitations in IR and NIR spectra of alunites. *Journal of Molecular Structure*, 480-481, 677-682.
- Brown, J.B. (1971) Jarosite-goethite stabilities at 25°C, 1 atm. *Mineralium Deposita*, 6, 245-252.
- Brunner, H., Ballhorn, R. and Schwab, R. (1987) Separation of cations, especially of radioelements, from aqueous solutions by crandallite-type compounds. Patent, NUKEM GmbH, Germany, 3 pp. (in German)
- Carpena, J. and Lacout, J.-L. (1997) From natural to synthetic apatites: the use of apatites as conditioning material for separated nuclear wastes. *Actualita Chimica*, 1997, 3-9.
- Cudennec, Y. and Bonnin, A. (1977) Préparation et étude de chromates d'aluminium et d'alcalin appartenant aux systèmes quaternaires M_2O , Al_2O_3 , CrO_3 , H_2O (M=Na, K). *Journal of Inorganic and Nuclear Chemistry*, 39, 155-156.
- Dutrizac, J.E. (1983) Factors affecting alkali jarosite precipitation. *Metallurgical Transactions B*, 14, 531-539.
- Dutrizac, J.E. (1984) The behaviour of impurities during jarosite precipitation. In *Hydrometallurgical Process Fundamentals* (Bautista, R.G. Ed.). Plenum Press, New York, NY, USA, 125-169.
- Dutrizac, J.E. (1997) The behavior of thallium during jarosite precipitation. *Metallurgical and Materials Transactions*

- tions B, 28, 765–776.
- Dutrizac, J.E. and Chen, T.T. (1981) The synthesis of mercury jarosite and the mercury concentration in jarosite-family minerals. *Canadian Mineralogist*, 19, 559–569.
- Dutrizac, J.E. and Chen, T.T. (2000) The behaviour of gallium during jarosite precipitation. *Canadian Metallurgical Quarterly*, 39, 1–14.
- Dutrizac, J.E. and Dinardo, O. (1983) The co-precipitation of copper and zinc with lead jarosite. *Hydrometallurgy*, 11, 61–78.
- Dutrizac, J.E. and Dou Mingmin (1993) The behaviour of indium during jarosite precipitation. In *World Zinc '93* (Matthew, I.G. Ed.). Australasian Institute Min. Metall., Parkville, Australia, 365–372.
- Dutrizac, J.E. and Jambor, J.L. (1987a) Behaviour of cesium and lithium during the precipitation of jarosite-type compounds. *Hydrometallurgy*, 17, 251–265.
- Dutrizac, J.E. and Jambor, J.L. (1987b) The behavior of arsenic during jarosite precipitation: arsenic precipitation at 97°C from sulfate or chloride media. *Canadian Metallurgical Quarterly*, 26, 91–101.
- Dutrizac, J.E. and Kaiman, S. (1976) Synthesis and properties of jarosite-type compounds. *Canadian Mineralogist*, 14, 151–158.
- Dutrizac, J.E. and Weatherell, C.J. (1989) The relative washing of zinc and cadmium from jarosite precipitates. CANMET MSL Division Report MSL 89-96 (TR), CANMET Corp., Ottawa, Canada, 9 pp.
- Dutrizac, J.E., Dinardo, O. and Kaiman, S. (1981) Selenate analogues of jarosite-compounds. *Hydrometallurgy*, 6, 327–337.
- Dutrizac, J.E., Hardy, D.J. and Chen T. (1996) The behaviour of cadmium during jarosite precipitation. *Hydrometallurgy*, 41, 269–285.
- Dymkov, Y., Holliger, P., Pagel, M., Gorshkov, A. and Artyukhina A. (1997) Characterization of a La-Ce-Sr-Ca aluminous hydroxy phosphate in nuclear zone 13 in the Oklo uranium deposit (Gabon). *Mineralium Deposita*, 32, 617–620.
- Earle, S.A., Ramirez, A.P. and Cava, R.J. (1999) The effect of gallium substitution for iron on the magnetic properties of hydronium iron jarosite. *Physica B*, 262, 199–204.
- Eighmy, T.T., Kinner, A.E., Shaw, E.L., Eusden, J.D., Jr. and Francis, C.A. (1999) Plumbogummite ($\text{PbAl}_3(\text{PO}_4)_2(\text{OH})_5 \cdot \text{H}_2\text{O}$) characterization by XPS: an environmentally important secondary mineral. *Surface Science Spectra*, 6, 202–209.
- Fehr, K.T., Hochleitner, R., Tippelt, G. and Amthauer, G. (2000) Kristallchemie von Mischkristallen der Reihe Plumbojarosit-Segninit. *European Journal of Mineralogy*, 12, Beiheft No. 1, 45.
- Foord, E.E. and Mills, B.A. (1978) Biaxiality in 'isometric' and 'dimetric' crystals. *American Mineralogist*, 63, 316–325.
- Fron del, C. (1958) Geochemical scavenging of strontium. *Science*, 128, 1623–1624.
- Gasharova, B., Göttlicher, J., Bernotat-Wulf, H. and Pentinghaus, H. (2000) Single crystal structure refinement and Raman spectra of synthetic natrojarosite ($\text{NaFe}_3(\text{SO}_4)_2(\text{OH})_6$) and $\text{KFe}_3(\text{CrO}_4)_2(\text{OH})_6$. *European Journal of Mineralogy*, 12, Beiheft No. 1, 54.
- Gaugglitz, R., Holterdorf, M., Franke, W. and Marx, G. (1992) Immobilization of heavy metals by hydroxylapatite. *Radiochimica Acta*, 58/59, 253–257.
- Ghobarkar, H., Schäf, O. and Guth, U. (1999) Zeolites—from kitchen to space. *Progress in Solid State Chemistry*, 27, 29–73.
- Gilkes, R. and Palmer, B. (1983) Synthesis, properties and dehydroxylation of members of the crandallite-goyazite series. *Mineralogical Magazine*, 47, 221–227.
- Giuseppetti, G. and Tadini, C. (1980) The crystal structure of osarizawaite. *Neues Jahrbuch für Mineralogie Monatshefte*, 1980, 401–407.
- Giuseppetti, G. and Tadini, C. (1987) Corkite $\text{PbFe}_3(\text{SO}_4)(\text{PO}_4)(\text{OH})_6$, its crystal structure and ordered arrangement of tetrahedral cations. *Neues Jahrbuch für Mineralogie Monatshefte*, 1987, 71–81.
- Giuseppetti, G. and Tadini, C. (1989) Beudantite $\text{PbFe}_3(\text{SO}_4)(\text{AsO}_4)(\text{OH})_6$, its crystal structure, tetrahedral site disordering and scattered Pb distribution. *Neues Jahrbuch für Mineralogie Monatshefte*, 1989, 27–33.
- Göttlicher, J. and Gasharova, B. (1999) Can jarosite be monoclinic? *European Journal of Mineralogy*, 11, Beiheft No. 1, 86.
- Goreaud, M. and Raveau, B. (1980) Alunite and crandallite: a structure derived from that of pyrochlore. *American Mineralogist*, 65, 953–956.
- Gorshkov, A. and Artyukhina, A. (1997) Characterization of a La-Ce-Sr-Ca aluminous hydroxy phosphate in nuclear zone 13 in the Oklo uranium deposit (Gabon). *Mineralium Deposita*, 32, 617–620.
- Gramaccioli, C.M., Campostrini, I. and Stara, P. (1997) Die Bacu Locci Mine (Villaputzu, Cagliari) auf Sardinien. *Lapis*, 22 (9), 13–26; 58.
- Harrison, A., Wills, A.S. and Ritter, C. (1997) Long-range order induced by diamagnetic dilution of jarosites, model Kagome antiferromagnets. *Physica B*, 241–243, 722–723.
- Hatch, L.P. (1953) Ultimate disposal of radioactive wastes. *American Scientist*, 41, 410–422. (cited in White and Kyle, 1995)
- Hendricks, S.B. (1937) The crystal structure of alunite and jarosite. *American Mineralogist*, 22, 773–784.
- Hintze, C. (1933) *Handbuch der Mineralogie*. Vol. I–4, Part 2. Walter de Gruyter & Co., Berlin, 721–741.
- Hladky, G. and Slansky, E. (1981) Stability of alunite minerals in aqueous solutions at normal temperature and pressure. *Bulletin de Minéralogie*, 104, 468–477.
- Hochleitner, R. and Fehr, K.T. (1996) Mischkristall-Beziehungen natürlicher Segninit-Plumbojarosit-Kintoreit-Mischkristalle aus Portugal. *European Journal of Mineralogy*, 8, Beiheft No. 1, 109.
- Hochleitner, R. and Fehr, K.T. (1998) Minerale der Beudantit-Gruppe als Speicherminerale für Blei und Arsen: Kristallchemische und kristallphysikalische Untersuchungen. *European Journal of Mineralogy*, 10, Beiheft No. 1, 132.
- Inami, T., Maegawa, S. and Takano, M. (1998) Neutron-diffraction study on Na- and K-jarosites. *Journal of Magnetism and Magnetic Materials*, 177–181, Pt. 1, 752–753.
- Jambor, J.L. (1999) Nomenclature of the alunite supergroup. *Canadian Mineralogist*, 37, 1323–1341.
- Jambor, J.L. (2000) Nomenclature of the alunite supergroup: reply. *Canadian Mineralogist*, 38, 1298–1303.

- Jambor, J.L. and Dutrizac, J.E. (1983) Beaverite-plumbojarosite solid solutions. *Canadian Mineralogist*, 21, 101–113.
- Jambor, J.L. and Dutrizac, J.E. (1985) The synthesis of beaverite. *Canadian Mineralogist*, 23, 47–51.
- Jambor, J.L., Owens, D.R., Grice, J.D. and Feinglos, M.N. (1996) Gallobaudantite, $\text{PbGa}_3[(\text{AsO}_4)(\text{SO}_4)]_2(\text{OH})_6$, a new mineral species from Tsumeb, Namibia, and associated new gallium analogues of the alunite-jarosite family. *Canadian Mineralogist*, 34, 1305–1315.
- Janeček, J. and Ewing, R.C. (1996) Florencite-(La) with fissionogenic REE from a natural fission reactor at Bangombé, Gabon. *American Mineralogist*, 81, 1263–1269.
- Johan, Z., Johan, V., Scharm, H. and Poucha, Z. (1995) Mineralogy and geochemistry of REE and Cr in Proterozoic cherts of Kokšín, Czech Republic. *Comptes Rendus de l'Académie des Sciences Paris*, 321, Sér. IIa, 1127–1138. (in French with English abstract)
- Jostons, A. and Kesson, S.E. (1994) The Synroc strategy for HLW management. *Mineralogical Magazine*, 58A, 458–459.
- Kamoun, F., Lorenz, M. and Kempe, G. (1989) Contributions to the formation of oxide iron(III) compounds in the presence of foreign cations. *Journal of Materials Science*, 24, 726–730.
- Karamanov, A., Cantalini, C., Pelino, M. and Hreglich, A. (1999) Kinetics of phase formation in jarosite glass-ceramic. *Journal of the European Ceramic Society*, 19, 527–533.
- Kato, T. and Miura, Y. (1977) The crystal structure of jarosite and svanbergite. *Mineralogical Journal*, 8, 419–430.
- Kharisun, Taylor, M.R., Bevan, D.J.M. and Pring, A. (1997) The crystal structure of kintoreite, $\text{PbFe}_3(\text{PO}_4)_2(\text{OH}, \text{H}_2\text{O})_6$. *Mineralogical Magazine*, 61, 123–129.
- Kolitsch, U. (1998) Bernalite from the Clara mine, Germany, and the incorporation of tungsten in minerals containing ferric iron. *Canadian Mineralogist*, 36, 1211–1216.
- Kolitsch, U. (1999) Arsenobismite discredited. *Neues Jahrbuch für Mineralogie Monatshefte*, 1999, 322–336.
- Kolitsch, U. and Elliott, P. (1999) Mineralogy of the Mount Malvern mine near Clarendon, South Australia. *Australian Journal of Mineralogy*, 5, 3–17.
- Kolitsch, U. and Pring, A. (1998) Kristallchemie von Gliedern der Crandallit- und Beudantitgruppe: Mögliche Speicherminerale für toxische Schwermetalle? *European Journal of Mineralogy*, 10, Beiheft No. 1, 161.
- Kolitsch, U., Slade, P.G., Tiekink, E.R.T. and Pring, A. (1999a) The structure of antimonian dussertite and the role of antimony in oxysalt minerals. *Mineralogical Magazine*, 63, 17–26.
- Kolitsch, U., Tiekink, E.R.T., Slade, P.G., Taylor, M. and Pring, A. (1999b) Hinsdalite and plumbogummite, their atomic arrangements and disordered lead sites. *European Journal of Mineralogy*, 11, 513–520.
- Kolitsch, U., Taylor, M., Fallon, G. and Pring, A. (1999c) Springcreekite, $\text{BaV}^{3+}_3(\text{PO}_4)_2(\text{OH}, \text{H}_2\text{O})_6$, a new member of the crandallite group, from the Spring Creek mine, South Australia: the first natural V^{3+} -member of the alunite family. *Neues Jahrbuch für Mineralogie Monatshefte*, 1999, 529–544.
- Lakshmi Reddy, S., Rao, P.S. and Reddy, B.J. (1991) Mössbauer, optical absorption and EPR spectra of Fe^{3+} in plumbo-jarosite minerals. *Physics Letters A*, 161, 74–76.
- Landa, E.R., Le, A.H., Luck, R.L. and Yeich, P.J. (1995) Sorption and coprecipitation of trace concentrations of thorium with various minerals under conditions simulating an acid uranium mill effluent environment. *Inorganica Chimica Acta*, 229, 247–252.
- Leclerc, A. (1980) Room temperature Mössbauer analysis of jarosite-type compounds. *Physics and Chemistry of Minerals*, 6, 327–334.
- Lengauer, C.L., Giester, G. and Irran, E. (1994) $\text{KCr}_3(\text{SO}_4)_2(\text{OH})_6$: Synthesis, characterization, powder diffraction data, and structure refinement by the Rietveld technique and a compilation of alunite-type compounds. *Powder Diffraction*, 9, 265–271.
- Levy, D.B., Custis, K.H., Casey, W.H. and Rock P.A. (1997) A comparison of metal attenuation in mine residue and overburden material from an abandoned copper mine. *Applied Geochemistry*, 12, 203–211.
- Lin, Z.X. and Herbert, R.B. (1997) Heavy metal retention in secondary precipitates from a mine rock dump and underlying soil, Dalarna, Sweden. *Environmental Geology*, 33, 1–12.
- Lottermoser, B.G. (1990) Rare-earth element mineralisation within the Mt. Weld carbonatite laterite, Western Australia. *Lithos*, 24, 151–167.
- Ma, Q.Y., Traina, S.J., Logan, T.J. and Ryan, J.A. (1993) In situ lead immobilization by apatite. *Environmental Science and Technology*, 27, 1803–1810.
- Mandarino, J.A. (1999) Fleischer's glossary of mineral species 1999. The Mineralogical Record Inc., Tucson, AZ, USA, 225 pp.
- Menchetti, S. and Sabelli, C. (1976) Crystal chemistry of the alunite series: crystal structure refinement of alunite and synthetic jarosite. *Neues Jahrbuch für Mineralogie Monatshefte*, 1976, 406–417.
- Moore, P.B. (1974) Derivative structures based on the alunite octahedral sheet; mitridatite and englishite. *Mineralogical Magazine*, 40, 863–866.
- Moore, P.B. and Araki, T. (1977) Mitridatite, $\text{Ca}_6(\text{H}_2\text{O})[\text{Fe}^{\text{III}}_9\text{O}_6(\text{PO}_4)_9] \cdot 3\text{H}_2\text{O}$. A noteworthy octahedral sheet structure. *Inorganic Chemistry*, 16, 1096–1106.
- Mordberg, L.E., Stanley, C.J. and Germann, K. (2000) Rare earth element anomalies in crandallite group minerals from the Schugorsk bauxite deposit, Timan, Russia. *European Journal of Mineralogy*, 12, 1229–1243.
- Morin, G., Juillot, F., Ildefonse, P., Calas, G., Samama, J.-C., Chevallier, P. and Brown, G.E., Jr. (2001) Mineralogy of lead in a soil developed on a Pb-mineralized sandstone (Largentière, France). *American Mineralogist*, 86, 92–104.
- Morteani, G. and Ackermann, D. (1996) Aluminium phosphates in muscovite-kyanite metaquartzites from Passo di Vizze (Alto Adige, NE Italy). *European Journal of Mineralogy*, 8, 853–869.
- Mumpton, F.A. (1999) *La roca magica*: Uses of natural zeolites in agriculture and industry. *Proceedings of the National Academy of Science, USA*, 96, 3463–3470.
- Mymrin, V. and Vazquez Vaamonde, A. (1999) New construction materials from Spanish jarosite processing wastes. *Minerals Engineering*, 12, 1399–1402.
- Norris, K. (1968) Some phosphate minerals of soils. In *Trans. 9th International Congress of Soil Science, Vol. II*

- (International Society of Soil Science Ed.). Adelaide, Australia, 713–723.
- Novák, F., Jansa, J. and Prachař, I. (1994) Classification and nomenclature of alunite–jarosite and related mineral groups. *Věstník Českého geologického ústavu*, 69, 51–57.
- Nriagu, J.O. (1984) Formation and stability of base metal phosphates in soils and sediments. In *Phosphate minerals* (Nriagu, J.O. and Moore, P.B. Eds.). Springer Verlag, Berlin, Germany, 318–329.
- Okada, K., Soga, H., Oosaka, J. and Otsuka, N. (1987) Syntheses of minamiite type compounds, $M_{0.5}Al_3(SO_4)_2(OH)_6$ with $M = Sr^{2+}, Pb^{2+}$ and Ba^{2+} . *Neues Jahrbuch für Mineralogie Monatshefte*, 1987, 64–70.
- Palache, C., Berman, C. and Frondel, C. (1951) Dana's system of mineralogy. 7th ed., Vol. II. John Wiley, New York, NY, USA, 1124 pp.
- Pöllmann, H. (1994a) Immobilization of pollutants in waste disposals by forming mineral reservoirs. In *Process Mineral. VII* (Petruk, W. and Rule, A.R. Eds.). The Minerals, Metals and Materials Society, Warrendale, PA, USA, 3–15.
- Pöllmann, H. (1994b) Immobile Fixierung von Schadstoffen in Speichermineralen. In *Geowissenschaften und Umwelt* (Matschullat, J. and Müller, G. Eds.). Springer-Verlag, Berlin, Germany, 331–340.
- Presant, E.W. and Tupper, W.M. (1966) The distribution and nature of arsenic in the soils of the Bathurst, New Brunswick, District. *Economic Geology*, 61, 760–767.
- Pring, A., Kolitsch, U. and Francis, G. (2000) Additions to the mineralogy of the Iron Monarch deposit, Middleback Ranges, South Australia. *Australian Journal of Mineralogy*, 6, 9–23.
- Radoslovich, E.W. (1982) Refinement of the gorceixite structure in Cm. *Neues Jahrbuch für Mineralogie Monatshefte*, 1982, 446–464.
- Radoslovich, E.W. and Slade, P.G. (1980) Pseudo-trigonal symmetry and the structure of gorceixite. *Neues Jahrbuch für Mineralogie Monatshefte*, 1980, 157–170.
- Rasmussen, B. (1996) Early diagenetic REE–phosphate minerals (florencite, gorceixite, crandallite, and xenotime) in marine sandstones: a major sink for oceanic phosphorus. *American Journal of Science*, 296, 601–632.
- Rasmussen, B., Buick, R. and Taylor, W.R. (1998) Removal of oceanic REE by authigenic precipitation of phosphatic minerals. *Earth and Planetary Science Letters*, 164, 135–149.
- Rattray, K.J., Taylor, M.R., Bevan, D.J.M. and Pring, A. (1996) Compositional segregation and solid solution in the lead dominant alunite–type minerals from Broken Hill, N.S.W. *Mineralogical Magazine*, 60, 779–785.
- Ringwood, A.E., Kesson, S.E., Ware, N.G., Hibberson, W. and Major, A. (1979) Immobilisation of high level nuclear reactor wastes in SYNROC. *Nature*, 278, 219–223.
- Roca, A., Vinals, J., Arranz, M. and Calero, J. (1999) Characterization and alkaline decomposition/cyanidation of beudantite–jarosite materials from Rio Tinto gossan ores. *Canadian Metallurgical Quarterly*, 38, 93–103.
- Rossmann, G.R. (1976) Spectroscopic and magnetic studies of ferric iron hydroxy sulfates: The series $Fe(OH)SO_4 \cdot nH_2O$ and the jarosites. *American Mineralogist*, 61, 398–404.
- Roy, D.M., Drafall, L.E. and Roy, R. (1978) Crystal chemistry, crystal growth, and phase equilibria of apatites. In *Phase diagrams—Materials science and technology*, Vol. 5 (Alper, A.M. Ed.). 186–236.
- Sanderson, I. and Wilson, C.W. (1994) Solving the jarosite issue. In *Proceedings 19th Annual Environmental Workshop 1994 Vol. 1* (Australian Mining Industry Council Ed.). Karratha, Western Australia, 9–14 Oct. 1994, 311–325.
- Sasaki, K., Tanaike, O. and Konno, H. (1998) Distinction of jarosite–group compounds by Raman spectroscopy. *Canadian Mineralogist*, 36, 1225–1235.
- Schukow, H., Breiting, D.K., Zeiske, Th., Kubanek, F., Mohr, J. and Schwab, R.G. (1999) Localization of hydrogen and content of oxonium cations of alunite via neutron diffraction. *Zeitschrift für Anorganische und Allgemeine Chemie*, 625, 1047–1050.
- Schuiling, R.D. and Van Gaans, P.F.M. (1997) The waste sulfuric acid lake of the TiO_2 –plant at Armyansk, Crimea, Ukraine. Part I. Self-sealing as an environmental protection mechanism. *Applied Geochemistry*, 12, 181–186.
- Schwab, R.G., Herold, H., Götz, C. and de Oliveira, N.P. (1990) Compounds of the crandallite type: Synthesis and properties of pure goyazite, gorceixite and plumbogumite. *Neues Jahrbuch für Mineralogie Monatshefte*, 1990, 113–126.
- Schwab, R.G., Götz, C., Herold, H., de Oliveira, N.P. (1993) Compounds of the crandallite group: Thermodynamic properties of Ca-, Sr-, Ba-, Pb-, La-, Ce- to Gd-phosphates and –arsenates. *Neues Jahrbuch für Mineralogie Monatshefte*, 1993, 551–568.
- Scorgie, D.E. (1991) Thallium in oxidized and unoxidized portions of an epithermal gold–silver deposit at the Buckhorn Mine, Eureka County, Nevada. Master's Thesis, Eastern Washington University, Cheney, WA, USA, 58 pp.
- Scott, K.M. (1987) Solid solution in, and classification of, gossan-derived members of the alunite–jarosite family, northwest Queensland, Australia. *American Mineralogist*, 72, 178–187.
- Scott, K.M. (2000) Nomenclature of the alunite supergroup: discussion. *Canadian Mineralogist*, 38, 1295–1297.
- Serna, C.J., Cortina, C.P. and Garcia Ramos, J.V. (1986) Infrared and Raman study of alunite–jarosite compounds. *Spectrochimica Acta*, 42A, 729–734.
- Shape Software (1999) ATOMS for Windows and Macintosh V5.0.4. Kingsport, TN, USA.
- Simoncini, B., Orru', R. and Cao, G. (1997) Self-propagating reactions for treating and recycling zinc hydrometallurgical wastes. *Key Engineering Materials*, 132–136, 2276–2279.
- Spotl, C. (1990) Authigenic aluminium phosphate–sulphates in sandstones of the Mitterberg Formation, Northern Calcareous Alps, Austria. *Sedimentology*, 37, 837–845.
- Stoffregen, R.E. and Cygan, G.L. (1990) An experimental study of the Na–K exchange between alunite and aqueous sulfate solutions. *American Mineralogist*, 75, 209–220.
- Suzuki, T., Ishigaki, K. and Ayuzawa, N. (1985) Removal of toxic lead(2+) ions by synthetic hydroxyapatites. *Chemical Engineering Communications*, 34, 143–151.
- Szymański, J.T. (1985) The crystal structure of plumbojarosite, $Pb[Fe_3(SO_4)_2(OH)_6]_2$. *Canadian Mineralogist*, 23, 659–668.
- Szymański, J.T. (1988) The crystal structure of beudantite $Pb(Fe,Al)_3[(As,S)O_4]_2(OH)_6$. *Canadian Mineralogist*,

- 26, 923–932.
- Tananaev, I.V., Kuznetsov, V.G. and Bol'shakova, N.K. (1967a) Basic gallium salts of the alunite type. *Russian Journal of Inorganic Chemistry*, 12, 28–30.
- Tananaev, I.V., Bolshakova N.K. and Kazakova, T.I. (1967b) Potassium gallium alum and its hydrolysis products. *Russian Journal of Inorganic Chemistry*, 12, 185–188.
- Traina, S.J. and Laperche, V. (1999) Contaminant bioavailability in soils, sediments, and aquatic environments. *Proceedings of the National Academy of Science, USA*, 96, 3365–3371.
- Vedanand, S., Rao, P.S., Reddy, Y.P., Nagarajan, T. and Reddy, B.J. (1992) Mossbauer, optical and EPR spectral studies of alunite. *Physica Scripta*, 45, 414–416.
- Walenta, K. (1966) Beiträge zur Kenntnis seltener Arsenatminerale unter besonderer Berücksichtigung von Vorkommen des Schwarzwalds. *Tschermaks Mineralogische und Petrographische Mitteilungen*, 11, 121–164.
- Walenta, K., Zwiener, M. and Dunn, P.J. (1982) Philipsbornit, ein neues Mineral der Crandallitreihe von Dundas auf Tasmanien. *Neues Jahrbuch für Mineralogie Monatshefte*, 1982, 1–5.
- Wang, R., Bradley, W.F. and Steinfink, H. (1965) The crystal structure of alunite. *Acta Crystallographica*, 18, 249–252.
- White, T. and Kyle, J. (1995) An appetite for toxic waste. *Chemistry in Australia*, 62, 39–40.
- White, T.J., Poniatowski, G., Eaton, G.F., Kyle, J.H., Lincoln, F. and Rodier, B.N. (1995) Xtalite—ecologically sustainable disposal of heavy metal smelting and refinery waste. In *Proceedings of the International Symposium on the Treatment and Minimization of Heavy Metal Containing Wastes* (Hager, J., Davidson, C.F., Mishra, B. and Litz, J.F. Eds.). The Minerals, Metals and Materials Society, Warrendale, PA, USA, 155–168.
- Wing, Y., Lal, M. and Howe, A.T. (1980) Proton conducting membranes composed of hydronium alunite. *Materials Research Bulletin*, 15, 1649–1654.
- Wise, W.S. (1975) Solid solution between the alunite, woodhouseite, and crandallite mineral series. *Neues Jahrbuch für Mineralogie Monatshefte*, 1975, 540–545.
- Xu, Y. and Schwartz, F.W. (1994) Lead immobilization by hydroxyapatite in aqueous solutions. *Journal of Contaminant Hydrology*, 15, 187–206.
- Yuh, Shang Jung and Rockett, T.J. (1981) The system CaO–Al₂O₃–P₂O₅–H₂O at 200°C. *Journal of the American Ceramic Society*, 64, 491–493.

Manuscript received; 21 November, 2000

Manuscript accepted; 16 April, 2001